

What is claimed is:

1. Low transmittance glass composed of soda-lime-silica glass,  
wherein said soda-lime-silica glass includes 0.001 to 2  
wt.%  $\text{Li}_2\text{O}$  and, as colorant, 0.7 to 2.2 wt.% total iron oxide  
5 expressed as  $\text{Fe}_2\text{O}_3$  (T- $\text{Fe}_2\text{O}_3$ ); and

wherein said glass has visible light transmittance (YA) of  
not greater than 65%, measured by using the CIE illuminant A,  
total solar radiation transmittance (TG) of not greater than 60%,  
and ultraviolet transmittance ( $T_{uv}$ ) defined by ISO 9050 of not  
10 greater than 25%, when said glass has a thickness between 2.1 mm  
and 6 mm.

2. Low transmittance glass as claimed in claim 1, wherein  $\text{Li}_2\text{O}$  is  
contained in an amount of less than 2 wt.%.

15

3. Low transmittance glass as claimed in claim 1, wherein  $\text{Li}_2\text{O}$  is  
contained in an amount of 0.05 to 0.5 wt.%.

4. Low transmittance glass as claimed in claim 1, wherein said  
20 low transmittance glass includes FeO expressed as  $\text{Fe}_2\text{O}_3$  in an  
amount of 20 to 50% of T- $\text{Fe}_2\text{O}_3$ .

5. Low transmittance glass as claimed in claim 1, wherein said  
low transmittance glass has base glass composition consisting  
25 essentially of:

65 to 80 wt.%  $\text{SiO}_2$ ;

0 to 5 wt.%  $\text{Al}_2\text{O}_3$ ;

0 to 10 wt.%  $\text{MgO}$ ;

5 to 15 wt.% CaO wherein a total amount of MgO and CaO is 5 to 15 wt.%; 10 to 20 wt.% Na<sub>2</sub>O;

0 to 5 wt.% K<sub>2</sub>O wherein a total amount of Na<sub>2</sub>O and K<sub>2</sub>O is 10 to 20 wt.%; and

5 0 to 5 wt.% B<sub>2</sub>O<sub>3</sub>.

6. Low transmittance glass as claimed in claim 1, wherein said low transmittance glass includes at least one selected from the group consisting of Se, CoO, Cr<sub>2</sub>O<sub>3</sub> and NiO as colorant.

10

7. Low transmittance glass as claimed in claim 6, wherein said low transmittance glass includes 0.0001 to 0.1 wt.% Se.

8. Low transmittance glass as claimed in claim 6, wherein said  
15 low transmittance glass includes 0.0001 to 0.1 wt.% CoO.

9. Low transmittance glass as claimed in claim 6, wherein said low transmittance glass includes 0.001 to 2 wt.% Cr<sub>2</sub>O<sub>3</sub>.

20 10. Low transmittance glass as claimed in claim 6, wherein said low transmittance glass includes 0.001 to 2 wt.% NiO.

11. Low transmittance glass as claimed in claim 1, wherein said low transmittance glass includes at least one selected from the  
25 group consisting of TiO<sub>2</sub>, CeO<sub>2</sub>, MoO<sub>3</sub>, V<sub>2</sub>O<sub>5</sub> and La<sub>2</sub>O<sub>3</sub> as colorant in an amount of 0.0001 to 1 wt.%.

12. Low transmittance glass as claimed in claim 1, wherein said low transmittance glass has visible light transmittance (YA) of

5 to 65%, measured by using the CIE illuminant A, total solar radiation transmittance (TG) of not greater than 50%, and ultraviolet transmittance (Tuv) defined by ISO 9050 not greater than 20%, when said glass has a thickness between 2.1 mm and 6 mm.